



Dow Corning® 902 RCS Joint Sealant Installation Guideline¹

Joint ² Opening	Sealant Thickness	Sealant Recess	Joint Opening Compression	Joint Opening Extension	Total Movement Range
1	1/2	1/2	1/2	2	1-1/2
1-1/2	1/2	1/2	3/4	3	2-1/4
2	1/2	1/2	1	4	3
2-1/2	1/2	1/2	1-1/4	5	3-3/4
3	1/2	5/8	1-1/2	6	4-1/2

¹ Table based on temperature of 77 degrees F. +/- 2 degrees and 50% RH +/- 5 %

² Mean opening (width at 77 degrees F. +/- 2 degrees and 50% RH +/- 5%)

For joints less than 1", or greater than 3" at time of sealing, contact Sealant Representative for recommendations.

If sealant is installed during cold weather (50 degrees F. or below), Sealant Representative should be contacted for specific installation instructions.

NOTE: ALL DIMENSIONS ARE IN INCHES.

Rev.
2/15/2000