



## **Dow Corning® 902 RCS Joint Sealant**

### **Joint Width vs Temperature**

#### **Recess Chart**

Joint Width At Time Of Sealing		Movement Rating (percent)	Recommended Recess Based On Temperature At Time Of Sealing (inches, min.)				
			< 40°F	40°-55°F	55°-75°F	75°-90°F	> 90°F
Inches	mm						
1.00	25.4	+100/-50	.625	.50	.50	.50	.50
1.25	31.8	+100/-50	.625	.50	.50	.50	.50
1.50	38.1	+100/-50	.625	.625	.50	.50	.50
1.75	44.5	+100/-50	.625	.625	.50	.50	.50
2.00	50.8	+100/-50	.625	.625	.50	.50	.50
2.25	57.2	+100/-50	.75	.625	.50	.50	.50
2.50	63.5	+100/-50	.75	.625	.50	.50	.50
2.75	69.9	+100/-50	.75	.75	.50	.50	.50
3.00	76.2	+100/-50	.75	.75	.50	.50	.50
3.25	82.6	±50	.75	.75	.625	.50	.50
3.50	88.9	±50	.75	.75	.625	.50	.50
3.75	95.3	±50	.75	.75	.625	.50	.50
4.00	101.6	±50	.75	.75	.625	.50	.50